

Technical Data Sheet

Product Description:

- DCEasy Primix all purpose Joint Compound is a specially formulated fiber reinforced, ready-to-use joint compound.
- It can be used for all types of boards (Gypsum/Calcium silicate /Fibre Cement etc.) without fibre tape or paper tape.
- It has minimal shrinkage and is crack resistant. It can also
- be used to patch and texture interior walls

Key Features -

For smooth, high-quality finishing of gypsum panel joints

- No Fibre Tape or Paper Tape required
- Excellent Workability, Easy application
- All Purpose
- Sandable
- Minimal Mixing, Ready-to-use
- Cracks Free

Recommended use -

- All types of Board Joints
- Fastener heads
- Metal corner beads

Application –

- 1)Surface must be clean & free from Dust.
- 2)It may have high viscosity in the pail, It may be diluted to workable viscosity by adding water followed by mechanical mixing
- 3)Apply compound evenly with a clean putty knife. Fill space between panels.
- 4)Allow to dry for approximately 24 hours for next coat or sanding
- 5)Thoroughly clean all tools & equipment's after use

Precaution & Limitations –

- Always use Clean Tools
- Do not mix with residues of previously used compounds
- It may appear thick in pail, to achieve desired consistency water can be added
- Mix This water gently, vigorous mixing will create bubbles.
- Do not overthin material, it may cause cracking & excessive shrinkage



**Packing Size –
1Kg, 2 Kg, 5Kg, 10 kg, 20 Kg**



Shelf Life:

- Shelf life is 1 Year from the date of manufacturing in unopened containers.
- Store at the cool and dry place, away from sun heat and under a shaded area.

Physical & Chemical Properties -

Appearance/Consistency	Creamy Paste
Volatile	Water
Odour	Mild
Solid	68 ± 0.6%
Dry Time	Approximately 8 to 24 hours Dry time varies with temperature, humidity, and depth of fill
Coverage	15 - 20 SqFt / Kg for Joints
Shelf Life	12 Month



EASY JOINT



ALCIBAY INDIA[®]